


Evidence of performance
Airborne sound insulation of building components

Test Report

No. GLA-1288.7/16Client**PRESS GLASS S.A.**Nowa Wieś
ul. Kopalniana 9
42-262 Poczesna

Product:	Laminated glass with acoustic interlayer
Construction:	16,76 <i>aku</i>
Designation:	VSG (FL 8/0,76 PVB SC/FL 8) kl.1/B/1
Dimension:	1230mm x 1480mm
Cross-section:	

<i>Rating</i>	R_w (C; C_{tr})	STC	OITC
<i>Basis</i>	PN-EN ISO 717-1: 2013	ASTM E413-10	ASTM E1332-10
<i>Value</i>	42 (0; -3) dB	42 dB	37 dB

Łozienica, 30.11.2016


PhD Krzysztof Mech
Head of Acoustics Laboratory